

BUILDWELL

GYPSUM PLASTER

**MILAYE
SIRF PAANI
LAGAYE BINA
PARESHAANI®**




Highlights

- ✓ Superior Whiteness
- ✓ No Shrinkage Cracks
- ✓ Imparts High Coverage
- ✓ No Water Curing Required

HOW TO APPLY



1 Clean the surface with sand paper/wire brush & then dampen it.



2 Use 1 part water & 1,5 part of Gypsum plaster.



3 Mix Buildwell Gypsum plaster in water to form uniform lump free paste.



4 Install the wooden strip / dhada or the leveling strip in the area where the ready paste is to be applied.



5 Apply the first coat approx upto 8 mm to 10 mm of thickness, before the 1st coat sets rake and cross rake the surface.



6 After drying for 72 hrs surface is now ready for painting.

TECHNICAL INFORMATION

PARAMETER	TEST METHOD	SPECIFICATION	RESULTS
Whiteness %	IS: 8042-1989	89 - 91	90.2
Workability	Internal	Good	Good
Residue on 200 mesh %	Internal	<3	0.9
Setting Time Min.	Internal	13-15	14

TECHNICAL SPECIFICATION

Appearance	Superior Whiteness
Pot Life	25 - 30 minutes
Coverage @ thickness of 10 mm.	20 - 25 Sq.ft./Bag of 25 Kg

KEY FEATURES

- Faster setting than the conventional sand cement plaster
- 50% lighter than sand cement plaster, reduces structural load on the building
- Direct application
- Compatible with all types of paints & decoratives
- Lowers paint consumption



STORAGE

