

# HOMESURE

TILE ADHESIVE

MILAYE  
SIRF PAANI  
LAGAYE BINA  
PARESHAANI®



20 Kg Bag | PACKAGING

## Highlights

- ✓ No Need For Hacking
- ✓ Highly Water Resistant
- ✓ Excellent Adhesion To Base Plaster/Concrete Surface
- ✓ Can Be Used On New As Well As Old Wall And Floor

## HOW TO APPLY



1 Clean the surface with sand paper/ putty blade & then dampen the surface.



2 Mix Tile Adhesive & water to obtain lump free paste. [Recommended mix 25-30% water]



3 After 10mins, Re-mix again for 2mins.



4 Apply first coat with putty blade.



5 With the help of notched 6mm trowel remove excess material prior placing the tiles.



6 Fix the tiles in place & tap gently with wooden hammer, Gently remove excess mixture from the tiles.

## TECHNICAL INFORMATION

TEST	TEST METHOD	RESULTS
Physical Appearance	Visual	Grey cementitious powder
Open Time	IS-15477-2004	> 20 minutes
Pot Life	Internal	> 30 minutes
Spreadability	Internal	Spread easily with good notchability
Adjustability	IS 15477:2004	10 minutes

PRODUCT	COVERAGE	USED FOR	APPROXIMATE WATER DEMAND
SILVER CLASS	2-3 sqft/kg for 3mm thickness	Ceramic tile	20kg - 5 to 5.5 liters 40kg - 10 to 11 liters

## KEY FEATURES

- High Durability
- Suitable for interior & exterior walls
- No shrinkage
- Saves time
- Increases productivity
- Cost-Effective
- No curing required
- Consistent work quality



STORAGE



## HOW TO APPLY



1 Clean the surface with sand paper/ putty blade & then dampen the surface.



2 Mix Tile Adhesive & water to obtain lump free paste. (Recommended mix Approx. 30% water)



3 After 10 minutes, remix again for 2 minutes.



4 Apply first coat with putty blade.



5 With the help of 6mm notch trowel remove excess material prior placing the tiles.



6 Fix the tiles in place & tap gently with wooden hammer. Gently remove excess mixture from the tiles.

**Note:** Maximum thickness should not be more than 3mm.

## TECHNICAL INFORMATION

TEST	TEST METHOD	RESULTS
Physical Appearance	Visual	Grey cementitious powder
Open Time	IS-15477-2004	>20 minutes
Pot Life	Internal	>30 minutes
Spreadability	Internal	Spread easily with good notchability
Adjustability	IS 15477:2004	10 minutes

PRODUCT	COVERAGE	USED FOR	APPROXIMATE WATER DEMAND
GOLD CLASS	2-3 sqft/kg for 3mm thickness	Vitrified tiles	20kg - 5 to 5.5 liters

## KEY FEATURES

- High durability
- Suitable for interior & exterior walls
- No shrinkage
- Saves time
- Increases productivity
- Cost-Effective
- No curing required
- Consistent work quality



STORAGE



## HOW TO APPLY



1 Clean the surface with sand paper/ putty blade & then dampen the surface.



2 Mix Tile Adhesive & water to obtain lump free paste. [Recommended mix Approx.30% water]



3 After 10 minutes, remix again for 2 minutes.



4 Apply first coat with putty blade.



5 With the help of 6mm notch trowel remove excess material prior placing the tiles.



6 Fix the tiles in place & tap gently with wooden hammer. Gently remove excess mixture from the tiles.

**Note:** Maximum thickness should not be more than 3mm.

## TECHNICAL INFORMATION

TEST	TEST METHOD	RESULTS
Physical Appearance	Visual	Grey cementitious powder
Open Time	IS-15477-2004	>20 minutes
Pot Life	Internal	>30 minutes
Spreadability	Internal	Spread easily with good notchability
Adjustability	IS 15477:2004	10 minutes

PRODUCT	COVERAGE	USED FOR	APPROXIMATE WATER DEMAND
PLATINUM CLASS	2-3 sqft/kg for 3mm thickness	Stones	20kg - 6 to 6.5 liters

## KEY FEATURES

- High durability
- Suitable for interior & exterior walls
- No shrinkage
- Saves time
- Increases productivity
- Cost-Effective
- No curing required
- Consistent work quality



STORAGE

